

Extragum Special Mineral PL

Description	High performance polyolefine APAO modified bitumen membrane for roofing works. This product is designed as base layer in a multi layer waterproofing systems for both new roofing works and refurbishment works. This product is also approved for foundation
CE	Single layer for roofing systems according with EN13707. Layer for pitch roofs according with EN13859.
Field of use	Exposed not-accessible roofs, technical roofs exposed or under heavy protection. Pitch roofs.
Certifications and Agreements	CE marking - FPC certificate number 1370-CPR-0042
Composition	<p>Top Surface: Mineral slate or Granules</p> <p>Back Surface: Film</p> <p>Reinforcement: Polyester reinforced with fiber glass</p>
Method of application	Fully torch applied



Dimension and packaging	Extragum Special Mineral	4PL
	Thickness (mm)	4,0 on selvedge
	Weight (kg/m ²)	5,4
	Rolls (m)	1X8

Property	Test Method	Unit	Value	Tolerance
Lenght	EN 1848-1	m	8,0	-1%
Width	EN 1848-1	m	1,0	-1%
Thickness on selvedge	EN 1849-1	mm	4,0	±0,2
Weight	EN 1849-1	Kg/m2	5,4	±10%
Tensile strength at max	EN 12 311-1	L x T (N/50mm)	900/700	-20%
Elongation at max	EN 12 311-1 1999	L x T (%)	50/50	-15
Nail tearing resistance	EN 12 310-1	L x T (N)	180/180	-30%
Static load	EN 12 730	Kg	25	≥
Resistance to impact	EN 12691	mm	1250	≥
Joints Shear resistance	EN 12317-1	N / 50mm	700	-20%
Flexibility at low temperature	EN 1109	(°C)	-20	≤
Flow resistance at elevated temperature	EN 1110	(°C)	140	≥
Dimensional stability	EN 1107-1	%	±0,3	≤
Flexibility at low temperature after thermal ageing	EN1296 EN 1109	(°C)	-20	+15
Flow resistance at elevated Temperature after thermal aeing	EN1296 EN 1110	(°C)	130	-10
Long exposure ageing - UV radiations combined with heat and water	EN1297 EN1850-1	-	NPD	-
Watertightness	EN 1928-B	kPa	60	≥
Reaction to fire	EN 13501-1	-	E	-
External fire performance	EN 13501-5	-	Froof	-

Storage

This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.

Modifications

Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the updated technical data sheet, please contact our technical department.