

# Gummiflex Antiradice PLA

<b>Description</b>	High performance APP modified bitumen membrane with antiroot agent for green roofs. This product is designed as top layer in a multi layer waterproofing systems for green roofs. This product is also approved for foundation waterproofing works.
<b>CE</b>	Top layer in a multi layer waterproofing systems according with EN13707 for flat roofs. Layer for foundation waterproofing works according with EN13969.
<b>Field of use</b>	Green roofs

<b>Certifications and Agreements</b>	CE marking - FPC certificate number 1370-CPR-0042.
--------------------------------------	--

<b>Composition</b>	<b>Top Surface:</b> Fine sand <b>Back Surface:</b> Film <b>Reinforcement:</b> Polyester reinforced with fiber glass
--------------------	---

<b>Method of application</b>	Fully torch applied
------------------------------	---------------------

<b>Dimension and packaging</b>	<b>Gummiflex Antiradice</b>	<b>3PLA</b>	<b>4PLA</b>
Thickness (mm)		3,0	4,0
Weight (kg/m2)		-	-
Rolls (m)		1X10	1X10



Property	Test Method	Unit	Value	Tolerance
Lenght	EN 1848-1	m	10	-1%
Width	EN 1848-1	m	1,0	-1%
Thickness	EN 1849-1	mm	3,0 / 4,0	±0,2
Weight	EN 1849-1	Kg/m2	NPD	±10%
Tensile strength at max	EN 12 311-1	L x T (N/50mm)	600/430	-20%
Elongation at max	EN 12 311-1 1999	L x T (%)	40/40	-15
Nail tearing resistance	EN 12 310-1	L x T (N)	150/150	-30%
Static load	EN 12 730	Kg	10	≥
Resistance to impact	EN 12691	mm	800	≥
Joints Shear resistance	EN 12317-1	N / 50mm	500/400	-20%
Flexibility at low temperature	EN 1109	(°C)	-10	≤
Flow resistance at elevated temperature	EN 1110	(°C)	120	≥
Dimensional stability	EN 1107-1	%	±0,3	≤
Watertightness	EN 1928-B	kPa	60	≥
Vapour Transmission (μ)	EN 1931	-	20000	≥
Root resistance	EN 13948	-	Passa/Passed	-
Reaction to fire	EN 13501-1	-	F	-
External fire performance	EN 13501-5	-	Roof	-

#### Storage

This product is packaged in rolls set up vertically on pallet or wooden box. It must be stored vertically under shelter, away from heat sources.

#### Modifications

Our company reserves the right to modify its composition as a result of technologic and experiments improvements. This product data sheet supersedes the previous edition, to obtain the updated technical data sheet, please contact our technical department.